General Purpose Acetoxy Silicone Adhesive Sealant

TE1254(N)

DESCRIPTION

TE1254(N) is a one-component, acetoxy cure, semi-flowable silicone adhesive sealant which cures at room temperature with moisture in the air. This product bonds to most materials, such as metals, plastics, ceramics and glass without the use of primers.

KEY FEATURES

- Primerless adhesion to many substrates
- Excellent high and low temperature resistance; from -55°C to 200°C continuous operation
- Excellent weatherability, ozone and chemical resistance
- Excellent electrical insulation properties
- Many color variations; Black Translucent, Grey and White
- Simple and easy-to-use; one component system

APPLICATIONS

- A waterproof sealant for electrical and communication equipments
- Air-tight sealants for meters to keep out water and dust
- Windshield sealants for automobiles and ships
- Oil leakage preventive sealants for automobile engine parts
- Sealing and potting to equipments which require cold and heat resistance
- General adhesion for metals, glass, plastic, wooden, etc

TYPICAL PROPERTY DATA

(JIS K 6249)

BOFORE CURING	
Appearance	Non flowing paste
Colours	Gray
Cure Type	Acetoxy
Specific Gravity at 25°C (g/ml) (standards ISO R 1183,DIN 53479,NMRPS 703)	0.999
Flowability (mm*mm/10g)	-
Viscosity (cps)	

CURING	
Tack-free Time (min) (23°C, 50%)	7
Cured thickness after 48h (mm) (23°C, 50%)	4.44

CURED PRODUCT	
Specific Gravity at 25°C (g/ml) (standards ISO2781,ASTM D297,BS 903 Part A1)	0.999
Shore A hardness (Standards ISO R868,DIN 53505,ASTM D 2240, BS 903 Part A7,NFT 46003,NMRPS 471)	24
Tensile Strength (kg.f/cm²) (Standards ISO R37(H2),DIN 53504,ASTM D 412, BS903 Part A2,NFT 46002(H2),NMRPS 470)	10.6
Elongtion at break (%) (Standards ISO R37(H2),DIN 53504,ASTM D 412, BS903 Part A2,NFT 46002(H2),NMRPS 470)	416
Dieletric strength (KV/mm) (standards NF C 26225,ASTM D 419,IEC 243)	23
Dieletric constant at 1 MHZ (standards NF C 26230,ASTM D 150,IEC 250)	3.5
Power factor at 1 KHZ (standards NF C 26250,ASTM D 150,IEC 250)	1.98x10 ⁻³
Volume resistivity,Ω.cm (standards NF C 26215,ASTM D 257,IEC 93)	1x10 ¹⁵

^{*} Testing is performed in accordance with current EST material test methods, laboratory

SPECIFICATION

Typical product data values should not be used as specification. Assistance and specification are available by contacting YanTai E.S.T. silicone technology co.,LTD

HANDLING AND SAFETY

When solvent are used, proper safety precautions must be considered toxic and must be used only in well ventilated areas.

USABLE LIFE AND STORAGE

When stored at or below 25°C (77°F) in the original unopened containers, this product has a usable life of 12 months from the date of manufacture.

^{*} Typical property data values should not be use as specifications

medical attention immediately.

5.See material safety data sheet.

CAUTION! HANDLING PRECAUTIONS FIRST AID MEASURES 1.FOR INDUSTRIAL USE 1. Wear suitable protective goggles, 1.Inhalation:Remove to fresh air and ONLY respirator and gloves. get medical attention immediately. 2.Use only where an adequate 2.Eye contact: Immediately flush eyes 2. This product is neither terted with plenty of water for at lest ventilation system is available to nor representde as suitable for medical or pharmaceutical uses. 15minutes.Get medical attention sxhaust poisonous gases. 3.After handling, wash face and hands immediately. 3.Do not use this product for very thoroughly. 3.Skin contact:Immediately flush skin other than its intended use,or Keep out of reach of children. user shall bear responsibility for with plenty of soop and water for at any problems. 5.Store in a cool,dark and dry place. least15minutes.Get medical attention immediatly. 4.Ingestion:Induce vomiting and get